

# Norton® FEP Fluoropolymer Film



Norton® FEP fluoropolymer film is manufactured from fluorinated ethylene propylene (FEP) resin by Saint-Gobain Films in four grades.

Norton® **FEP Type FG** utilizes the low dielectric constant and dissipation over a wide range of temperatures and frequencies for low signal distortion and attenuation in flexible printed circuit and flat cable applications. The high surface and volume resistivity minimizes current leakage and provides excellent insulation in wire and cable applications.

Norton® FEP also provides the chemical and thermal resistance to withstand aggressive environments, making it an excellent candidate for diaphragms, gaskets, protective linings, sample bags, and containers. Fabricated shapes and contours can be produced via heat sealing and thermoforming. The outstanding weatherability and optical properties of Norton® FEP film provide excellent performance in environmental growth chambers and solar collectors.

Norton® **FEP Type FS** is a translucent film made from high molecular weight resin for applications where high flex life and stress-crack-resistant performance are required, such as tank linings and diaphragms.

Norton® **FEP Type RF** is a clear or pigmented film designed for release applications. The non-stick surface, chemical resistance, and 205°C (400°F) usage temperature make Norton® FEP an ideal release film for composite molding over a wide range of resin systems. High elongation and a smooth, low-gel film surface allow Norton® FEP to conform to complex mold contours and produce a smooth part finish. Perforated film is available to control outgassing and resin bleed. Pigmented films increase visibility to speed removal from parts and mold.

Norton® **FEP Type WF** (mechanical grade) film is an ideal economical solution for applications that don't require high aesthetic standards, such as hot melt adhesive (welding tape) application. FEP WF film possesses all physical, mechanical, and thermal properties of FEP FG grade, while offering up to 15% savings.


Norton® is a registered trademark.

## Features/Benefits

- Outstanding anti-stick release properties
- Performance from -254°C (-425°F) to 205°C (400°F)
- Exceptional chemical resistance and electric properties
- Complies with FDA requirements
- Product thicknesses from 0.0005" (0.013 mm) to 0.030" (0.76 mm)
- Widths up to 62" (1575 mm) for 0.0005" to 0.010" and up to 48" for over 0.010" thick
- Optically transparent and pigmented
- All films are manufactured and converted in class 100,000 clean room facility
- Available in cementable (surface treated) form



Superior chemical resistance and clarity



High temperature resistance and non-wetting surface for gas sampling bags

## Norton® FEP Fluoropolymer Film — Typical Physical Properties\*

Property	ASTM Method	Metric Value	Metric Units	English Value	English Units
<b>General</b>					
Specific Gravity	D-792	2.12-2.17		2.12-2.17	
Yield (1 mil film)		18	m <sup>2</sup> /kg	90	ft <sup>2</sup> /lb
Flammability	UL-94	V-0		V-0	
Water Absorption		<0.01	%	<0.01	%
<b>Mechanical</b>					
Tensile Strength @ Break	D-882	24	MPa	3500	psi
Elongation @ Break	D-882	300	%	300	%
Tensile Modulus	D-882	480	MPa	70000	psi
Initial Tear Strength, 1 mil	D-1004	2.2-2.7	N	0.5-0.6	lb <sub>f</sub>
Initial Tear Strength, 2 mil	D-1004	4.9-5.3	N	1.1-1.2	lb <sub>f</sub>
Propagating Tear Strength, 1 mil	D-1922	1.4-1.5	N	0.32-0.33	lb <sub>f</sub>
Propagating Tear Strength, 2 mil	D-1922	2.4-2.7	N	0.55-0.60	lb <sub>f</sub>
Fold Endurance (M.I.T.)	D-2176	10000	cycles	10000	cycles
<b>Electrical</b>					
Dielectric Strength, 1 mil	D-149	240	kV/mm	6000	V/mil
Dielectric Constant, 1 kHz	D-150	2.1		2.1	
Dissipation Factor, 1 kHz	D-150	0.0003		0.0003	
<b>Thermal</b>					
Melt Point	D-3418	252-282	°C	485-540	°F
Maximum Continuous Service Temperature		205	°C	400	°F
Specific Heat		1172	J/(kg•°K)	0.28	Btu/(lb•°F)
Coefficient of Thermal Conductivity		0.195	W/(m•°K)	1.35	Btu•in/(hr•ft <sup>2</sup> •°F)
Coefficient of Linear Thermal Expansion	D-696	9.9 x 10 <sup>-5</sup>	mm/(mm•°C)	5.5 x 10 <sup>-5</sup>	in/(in•°F)
Limiting Oxygen Index	D-2863	95	%	95	%
<b>Optical</b>					
Refractive Index	D-542	1.341-1.347		1.341-1.347	
Solar Transmission	E-424	96	%	96	%

\*Represent typical performance properties and should not be used for specification purposes. Contact your Saint-Gobain Performance Plastics representative for appropriate values.



### PERFORMANCE PLASTICS

Saint-Gobain Performance Plastics  
Films—The Americas  
150 Dey Road  
Wayne, NJ 07470-4699  
Phone: (800) 526-7844  
Fax: (973) 696-4056

Saint-Gobain Performance Plastics  
Films—Asia  
Suite 1203, No. 147  
Chienkwo North Road Section 2  
Taipei Taiwan, 104  
Taiwan  
Tel: 886 (2) 25034201  
Fax: 886 (2) 25034202

Saint-Gobain Performance Plastics,  
Tygaflo® Ltd  
Films—Europe  
Bay 3, Transpennine Estate, Gorrels Way  
Rochdale Lancashire OL11 2PX  
United Kingdom  
Tel: (44) 1706 746900  
Fax: (44) 1706 746991

**Limited Warranty:** For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics Corporation warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential, arising out of the use, misuse, or inability to use this product(s). SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.



**NOTE:** Saint-Gobain Performance Plastics Corporation does not assume any responsibility or liability for any advice furnished by it, or for the performance or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and/or user. The purchaser and/or user should perform its own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.