



# DuPont™ Kapton® FN

## POLYIMIDE FILM

### Technical Data Sheet

DuPont™ Kapton® FN is a general purpose HN film that is coated or laminated on one or both sides with Teflon® FEP fluoropolymer. Kapton® FN imparts heat sealability, provides a moisture barrier, and enhances chemical resistance.

Kapton® FN is recommended in applications that require a heat bondable film, or moisture and chemical resistance beyond the capabilities of uncoated Kapton® films.

Techniques for fabricating DuPont™ Teflon® FEP can be found in technical data bulletin H-55005-2. Chemical resistance data for Teflon® FEP can be found in information bulletin H-55007-2.

#### Applications

- Tubing
- Heater circuits
- Heat sealable bags
- Automotive diaphragms and manifolds
- Electrical insulation

#### Product Specifications

Kapton® FN is manufactured, slit and packaged according to the product specifications listed in H-38479, Bulletin GS-96-7.

#### Certification

Kapton® FN meets ASTM D-5213 (type 2, item A) and IPC 4202/1 requirements.



*The miracles of science™*

**Table 1**  
**Physical Properties of Kapton® FN Film**

Property	Typical Value for Film Type*			Test Method
	120FN616	150FN019	250FN029	
Ultimate Tensile Strength, MPa (psi) 23°C (73°F) 200°C (392°F)	207 (30,000) 121 (17,500)	162 (23,500) 89 (13,000)	200 (29,000) 115 (17,000)	ASTM D-889-91, Method A*
Yield Point at 3%, MPa (psi) 23°C (73°F) 200°C (392°F)	61 (9000) 42 (6000)	49 (7000) 43 (6000)	58 (8500) 36 (5000)	ASTM D-889-91, Method A
Stress at 5% Elongation, MPa (psi) 23°C (73°F) 200°C (392°F)	79 (11,500) 53 (8000)	65 (9500) 41 (6000)	76 (11,000) 48 (7000)	ASTM D-889-91, Method A
Ultimate Elongation, % 23°C (73°F) 200°C (392°F)	75 80	70 75	85 110	ASTM D-889-91, Method A
Tensile Modulus, GPa (psi) 23°C (73°F) 200°C (392°F)	2.48 (360,000) 1.62 (235,000)	2.28 (330,000) 1.14 (165,000)	2.62 (380,000) 1.38 (200,000)	ASTM D-889-91, Method A
Impact Strength at 23°C (73°F), N•cm (ft•lb)	78 (0.58)	68.6 (0.51)	156.8 (1.16)	ASTM D-889-91, Method A
Tear Strength, initial Graves, N (lbf)	11.8 (2.6)	11.5 (2.6)	17.8 (4.0)	ASTM D-889-91, Method A
Tear Strength, propagating Elmendorf, N	7.2	16.3	26.3	ASTM D-889-91, Method A
Polyimide, wt% FEP, wt%	80 20	57 43	73 27	ASTM D-889-91, Method A
Density, g/cc or g/mL	1.53	1.67	1.57	ASTM D-889-91, Method A

\*Specimen size 25 x 150 mm (1.6 in); jaw separation 100 mm (4 in), jaw speed, 50mm/min (2 in/min). Ultimate refers to the tensile strength and elongation measured at break.

**Table 2**  
**Typical Electrical Properties of Kapton® FN Film at 23°C (73°F), 50% RH**

Property	120FN616	150FN019	250FN029	Test Method
Dielectric Strength, V/μm (V/mil)	272 (6900)	197 (5000)	197 (5000)	ASTM D-149-91
Dielectric Constant	3.1	2.7	3.0	ASTM D-150-92
Dissipation Factor	0.0015	0.0013	0.0013	ASTM D-150-92
Volume Resistivity, Ω•cm 23°C (73°F) 200°C (392°F)	1.4 x 10 <sup>17</sup> 4.4 x 10 <sup>14</sup>	2.3 x 10 <sup>17</sup> 3.6 x 10 <sup>14</sup>	1.9 x 10 <sup>17</sup> 3.7 x 10 <sup>14</sup>	ASTM D-257-91

**Table 3**  
**Chemical Properties of Kapton® FN Film**

Property	120FN616	150FN019	400FN022	Test Method
Moisture Absorption, % at 23°C (73°F), 50% RH 98% RH	1.3 2.5	0.8 1.7	0.4 1.2	ASTM D-570
Water Vapor Permeability, g/(m <sup>2</sup> •24 h) g/(100 in <sup>2</sup> •24 h)	17.5 1.13	9.6 0.62	2.4 0.16	ASTM E-96-92

For more information on DuPont™ Kapton® or other High Performance Materials, please contact your local representative, or visit our website for additional regional contacts:

### Americas

DuPont High Performance Materials  
U.S. Rt. 23 & DuPont Road  
Circleville, OH 43113  
Tel: 800-967-5607

### Europe

DuPont de Nemours (Luxembourg) S.A.R.L.  
Rue General Patton  
L-2984 Luxembourg  
Tel: 352-3666-5935

### Asia

DuPont Taiwan  
No. 45, Hsing-Pont Road  
Taoyuan, Taiwan, R.O.C.  
Tel: 886-3-3773668

### Japan

DuPont-Toray Co., Ltd.  
5-6 Nihonbashi Honcho 1-chome  
Chuo-ku, Tokyo 103-0023 Japan  
Tel: 81-3-3245-5061

[kapton.dupont.com](http://kapton.dupont.com)

Copyright ©2006 DuPont or its affiliates. All rights reserved. The DuPont Oval, DuPont™, The miracles of science™, Kapton® and Teflon® are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates. NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF DUPONT.

Caution: Do not use in medical applications involving permanent implantation in the human body, or contact with internal body fluids or tissues. For other medical applications, see "DuPont Medical Caution Statement," H-50102.

This information is based on data believed to be reliable, but DuPont makes no warranties, express or implied, as to its accuracy and assumes no liability arising out of its use. The data listed herein falls within the normal range of product properties but should not be used to establish specification limits or used alone as the basis of design. Because DuPont cannot anticipate or control the many different conditions under which this information and/or product may be used, it does not guarantee the usefulness of the information or the suitability of its products in any given application. Users should conduct their own tests to determine the appropriateness of the product for their particular purposes.



*The miracles of science™*